



USES:
PA-750 PROTECTION COURSE

PA-750® PROTECTION COURSE S

Commercial Product Data Sheet

PA-750® Protection Course S is the lightly modified asphalt coated fiberglass sheet designed as a protection layer for use with PA-750 Hot-Applied Rubberized Waterproofing Systems. PA-750 Protection Course S consists of a lightweight random fibrous glass mat impregnated and coated with quality styrene-butadiene-styrene (SBS) modified bitumen and asphalt.

Contact Siplast for information on approved product uses.

PRODUCT INFORMATION

Roll Length	Min: 102.3 ft (31.2 m)
Roll Width	Avg: 3.28 ft (1.00 m)
Coverage	3 Squares (27.9 m ²)
Coverage Weight Per Square	Min: 30 lb (1.3 kg/m ²)
Thickness	Avg: 47 mils (1.2 mm) Min: 39 mils (1.0 mm)
Laying Lines	3 in (7.6 cm) & 13 5/8 in (34.6 cm) Line Color: Blue
Top Surfacing	Silica Parting Agent
Back Surfacing	Silica Parting Agent

Application

Refer to the applicable Siplast Technical Guide for detailed application information.

Storage and Handling

All Siplast roll roofing products should be stored on end on a clean flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet
Rolls Per Pallet: 20
Pallets Per Truckload: 18
Minimum Roll Weight: 90 lb (40.8 kg)