


**USES:
FINISH PLY**

PARADIENE® 30 FR

Commercial Product Data Sheet

Paradiene 30 FR is the modified bitumen finish ply of the Paradiene 20/30 FR System. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paradiene 30 FR consists of a lightweight random fibrous glass mat impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen and is surfaced with ceramic granules.

Contact Siplast for information on approved product uses.

PRODUCT INFORMATION

Standards	ASTM D6163 Type I, Grade G; CSA A123.23-15 Type A, Grade 1
Roll Length	Min: 33.5 ft (10.21 m)
Roll Width	Avg: 3.28 ft (1.00 m)
Coverage	1.0 Square (9.3 m ²)
Coverage Weight Per Square	Min: 90 lb (4.4 kg/m ²)
Selvage Width	Avg. 2.75 in (70 mm) Orange laying line is 3 in (76 mm) from the edge of the sheet.
Selvage Surfacing	Silica Parting Agent
Top Surfacing	No. 11 Ceramic Granules (Standard color finish is #A-720 White)
Back Surfacing	Silica Parting Agent
Product Options	RoofTag, Eco Activ Granules, Special Colors

Application

Refer to the Siplast Technical Guide for detailed application information and slope limitations. Paradiene 30 FR is lapped 3 inches (76 mm) side and end.



Storage and Handling

All Siplast roll roofing products should be stored on end on a clean, flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging


Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet
Rolls Per Pallet: 23
Pallets Per Truckload (Typical): 18
Minimum Roll Weight: 90 lb (40.8 kg)

Listings, Approvals, & Certifications



Current copies of all Siplast Commercial Product Data Sheets & Safety Data Sheets are posted on our website at www.siplast.com
Rev Date 10/2022

U.S. TEST STANDARDS

Property (as Manufactured)	Values / Units		Test Method
Thickness (average)	130 mils (3.3 mm)		ASTM D5147 Section 6
*Thickness at Selvage	98 mils (2.5 mm) avg.	94 mils (2.4 mm) min.	ASTM D5147 Section 6
**Peak Load @ 73.4°F (23°C) (average)	30 lbf/inch (5.3 kN/m)		ASTM D5147 Section 7
**Peak Load @ 0°F (-18°C) (average)	75 lbf/inch (13.2 kN/m)		ASTM D5147 Section 7
**Elongation @ Peak Load 73.4°F (23°C) (average)	3%		ASTM D5147 Section 7
**Elongation @ Peak Load 0°F (-18°C) (average)	3%		ASTM D5147 Section 7
**Ultimate Elongation @ 73.4°F (23°C) (average)	55%		ASTM D5147 Section 7
**Tear Strength (average)	40 lbf (0.18 kN)		ASTM D5147 Section 8
Water Absorption (maximum)	1%		ASTM D5147 Section 10
Dimensional Stability (maximum)	0.1%		ASTM D5147 Section 11
Low Temperature Flexibility (maximum)	-15°F (-26°C)		ASTM D5147 Section 12
Granule Embedment	1.5 grams per sample Max. avg. loss	2.0 grams per sample Max. individual loss	ASTM D5147 Section 15
Compound Stability (minimum)	250°F (121°C)		ASTM D5147 Section 16
Cyclic Fatigue	Paradiene 30 finish ply bonded to Paradiene 20 base ply, with an approved method of attachment, passes ASTM D5849 both as-manufactured and after heat conditioning according to ASTM D5147.		
*Measured on the selvage edge excluding the granule surfacing. **The value reported is the lower of either MD or XD.			The above properties have been validated by PRI and are under continuous follow-up to ensure compliance. The product has been validated to meet ASTM D6163-08, Type I, Grade G.

CANADA TEST STANDARDS

Property (as Manufactured)	Values / Units		Test Method
Thickness (average)	3.3 mm (130 mils)		CSA A123.23-15
*Thickness at Selvage	2.5 mm (98 mils) avg.	2.4 mm (94 mils) min.	CSA A123.23-15
**Peak Load @ 23°C (73.4°F) (average)	5.3 kN/m (30 lbf/inch)		CSA A123.23-15
**Peak Load @ -18°C (0°F) (average)	13.2 kN/m (75 lbf/inch)		CSA A123.23-15
**Elongation @ Peak Load 23°C (73.4°F) (average)	3%		CSA A123.23-15
**Elongation @ Peak Load -18°C (0°F) (average)	3%		CSA A123.23-15
**Ultimate Elongation @ 23°C (73.4°F) (average)	55%		CSA A123.23-15
Dimensional Stability	0.1%		CSA A123.23-15
Low Temperature Flexibility (maximum)	-26°C (-15°F)		CSA A123.23-15
Granule Embedment	1.5 grams per sample Max. avg. loss	2.0 grams per sample Max. individual loss	CSA A123.23-15
Compound Stability (minimum)	121°C (250°F)		CSA A123.23-15
*Measured on the selvage edge excluding the granule surfacing. **The value reported is the lower of either MD or XD.			