



## PARAFOR® 30 TG BW

### Commercial Product Data Sheet

Parafor® 30 TG BW is the modified bitumen finish ply designed for use in homogeneous multi-layer modified bitumen roof membrane systems. Parafor 30 TG BW consists of a fiberglass scrim/polyester mat composite impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen and is surfaced with highly reflective, white mineral granules. The back of the sheet is coated with a modified bitumen asphalt layer specifically formulated for torch application, is embossed with a grooved pattern, and is surfaced with a polyolefin burn-off film.

Contact Siplast for information on approved product uses.

#### USES: FINISH PLY FLASHING SHEET

### PRODUCT INFORMATION

#### Application

Refer to the Siplast Technical Guide for detailed application information and slope limitations. Parafor 30 TG BW is lapped 3 inches (76.2 mm) at sides and 6 inches (152 mm) at ends.



#### Storage and Handling

All Siplast roll roofing products should be stored on end on a clean, flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

#### Packaging

Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet  
Rolls Per Pallet: 20  
Pallets Per Truckload: 18  
Minimum Roll Weight: 104 lb (47.1 kg)

#### Listings, Approvals, & Certifications



Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.  
FM Approved - Refer to RoofNav.com for specific assemblies.

Standards	ASTM D6162 Type II, Grade G; CSA A123.23-15 Type B, Grade 1
Roll Length	Min: 32.8 ft (10.0 m)
Roll Width	Avg: 39.4 in (1.0 m)
Coverage	0.98 Square (97.9 ft²) (9.1 m²)
Coverage Weight Per Square	Min: 106 lb (5.2 kg/m²)
Selvage Width	Avg. 2.75 in (70 mm) Orange laying line is 3 in (76.2 mm) from the edge of the sheet.
Selvage Surfacing	Polyolefin Burn-off Film
Top Surfacing	Bright White Mineral Granules
Back Surfacing	Polyolefin Burn-off Film
Product Options	RoofTag

## U.S. TEST STANDARDS

Property (as Manufactured)	Values / Units		Test Method
Thickness (average)	161 mils (4.1 mm)		ASTM D5147 Section 6
Thickness at Selvage	122 mils (3.1 mm) avg.	118 mils (3.0 mm) min.	ASTM D5147 Section 6
*Peak Load @ 73.4°F (23°C) (average)	80 lbf/inch (14.0 kN/m)		ASTM D5147 Section 7
*Peak Load 0°F (-18°C) (average)	125 lbf/inch (21.9 kN/m)		ASTM D5147 Section 7
*Elongation @ Peak Load 73.4°F (23°C)	40%		ASTM D5147 Section 7
*Elongation @ Peak Load 0°F (-18°C) (average)	40%		ASTM D5147 Section 7
*Ultimate Elongation @ 73.4°F (23°C)	90%		ASTM D5147 Section 7
*Tear Strength (average)	100 lbf (0.45 kN)		ASTM D5147 Section 8
Water Absorption (maximum)	1%		ASTM D5147 Section 10
Dimensional Stability (maximum)	0.5%		ASTM D5147 Section 11
Low Temperature Flexibility (maximum)	-15°F (-26°C)		ASTM D5147 Section 12
Granule Embedment	1.5 grams per sample Max. avg. loss	2.0 grams per sample Max. individual loss	ASTM D5147 Section 15
Compound Stability (minimum)	250°F (121°C)		ASTM D5147 Section 16
Cyclic Fatigue	Parafor 30 TG BW utilized as a single-layer membrane or bonded to an acceptable Paradiene 20 base ply, with an approved method of attachment, passes ASTM D5849 both as manufactured and after heat conditioning according to ASTM D5147.		

\*The value reported is the lower of either MD or XD.

## CANADA TEST STANDARDS

Property (as Manufactured)	Values / Units		Test Method
Thickness (average)	161 mils (4.1 mm)		CSA A123.23-15
Thickness at Selvage	3.1 mm (122 mils) avg.	3.0 mm (118 mils) min.	CSA A123.23-15
*Peak Load @ 23°C (73.4°F) (average)	14.0 kN/m (80 lbf/inch)		CSA A123.23-15
*Peak Load @ -18°C (0°F)	21.9 kN/m (125 lbf/inch)		CSA A123.23-15
*Elongation @ Peak Load 23°C (73.4°F) (average)	40%		CSA A123.23-15
*Elongation @ Peak Load - 18°C (0°F) (average)	40%		CSA A123.23-15
*Ultimate Elongation @ 23°C (73.4°F)	90%		CSA A123.23-15
Strain energy before and after conditioning @ 23°C (73.4°F) @ -18°C (0°F)	≥5.5 kN/m (≥31 lbf/in), ≥3.0 kN/m (≥17 lbf/in)		CSA A123.23-15
Dimensional Stability (maximum)	0.5%		CSA A123.23-15
Low Temperature Flexibility (maximum)	-26°C (-15°F)		CSA A123.23-15
Granule Embedment	1.5 grams per sample Max. avg. loss	2.0 grams per sample Max. individual loss	CSA A123.23-15
Compound Stability (minimum)	121°C (250°F)		CSA A123.23-15
Mass Per Unit Area (minimum)	5.0 kg/m² (104 lb/sq)		CSA A123.23-15

\*The value reported is the lower of either MD or XD.

## SOLAR REFLECTANCE / THERMAL EMITTANCE

Property (as Manufactured)	Values	Test Method
Solar Reflectance (avg.)	0.74	ASTM C1549
Thermal Emittance (avg.)	0.91	ASTM C1371
Solar Reflectance Index (avg.)	92	ASTM E1980