



**USES:**  
**BASE PLY**  
**FLASHING REINFORCING SHEET**

## PARATECH 180 BASE TG

### Commercial Product Data Sheet

Paratech 180 Base TG is the modified bitumen base ply of the Paratech two-ply modified bitumen roof system. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paratech 180 Base TG consists of a 180-gram polyester mat impregnated and coated with styrene-butadiene-styrene (SBS) modified bitumen. The top surface is covered with a mineral parting agent and the back surface is coated with an SBS modified bitumen adhesive layer specifically formulated for torch applications with a polyolefin film bottom surface.

Contact Siplast for information on approved product uses.

### PRODUCT INFORMATION

Standards	ASTM D6164 Type I, Grade S; CSA A123.23-15 Type B, Grade 3
Roll Length (nominal)	32.8 ft (10 m)
Roll Width (nominal)	3.28 ft (1.0 m)
Coverage Per Roll (Typical with 3" Side & End Laps)	0.979 Squares (9.1 m <sup>2</sup> )
Coverage Weight Per Square (nominal)	82 lb (4.03 kg/m <sup>2</sup> )
Laying Lines (nominal)	3 in (76 mm) Line Color: White
Top & Back Surfacing	Mineral Parting Agent Polyolefin Film

#### Application

Refer to the Siplast specifications for detailed application information and slope limitations. Paratech 180 Base TG is lapped 3 inches (76 mm) side and end.



#### Storage and Handling

All Siplast roll roofing products should be stored on end on a clean flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

#### Packaging

Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet  
 Rolls Per Pallet: 25  
 Pallets Per Truckload: 21  
 Roll Weight (nominal): 81 lb (36.7 kg)

#### Listings, Approvals, & Certifications



### U.S. TEST STANDARDS

Property (as Manufactured)	Values / MD	Values / XMD	Test Method
Thickness (average)	118 mils (3.0 mm)		ASTM D5147
Peak Load @ 73.4°F (23°C) (average)	85 lbf/in	65 lbf/in	ASTM D5147
Peak Load @ 0°F (-18°C) (average)	115 lbf/in	90 lbf/in	ASTM D5147
Elongation @ Peak Load 73.4°F (23°C) (average)	55%	60%	ASTM D5147
Elongation @ Peak Load 0°F (-18°C) (average)	35%	40%	ASTM D5147
Ultimate Elongation 73.4°F (23°C)	65%	80%	ASTM D5147
Tear Strength (average)	125 lbf	85 lbf	ASTM D5147
Water Absorption (maximum)	1%		ASTM D5147
Low Temperature Flexibility (maximum)	-15°F (-26°C)	-15°F (-26°C)	ASTM D5147
Dimensional Stability (maximum)	<0.5%	<0.5%	ASTM D5147
Compound Stability (minimum)	240°F (116°C)		ASTM D5147

### CANADA TEST STANDARDS

Property (as Manufactured)	Values / MD	Values / XMD	Test Method
Thickness (average)	3.0 mm (118 mils)		CSA A123.23-15
Strain Energy 23°C (73.4°F) (minimum)	8.0 kN/m	7.0 kN/m	CSA A123.23-15
Strain Energy -18°C (0°F) (minimum)	8.0 kN/m	7.0 kN/m	CSA A123.23-15
Peak Load @ 23°C (73.4°F) (average)	14.9 kN/m	11.4 kN/m	CSA A123.23-15
Peak Load @ -18° (0°F) (average)	20.1 kN/m	15.8 kN/m	CSA A123.23-15
Elongation @ Peak Load 23°C (73.4°F) (average)	55%	60%	CSA A123.23-15
Elongation @ Peak Load -18°C (0°F) (average)	35%	40%	CSA A123.23-15
Low Temperature Flexibility (maximum)	-26°C (-15°F)	-26°C (-15°F)	CSA A123.23-15
Dimensional Stability (maximum)	<0.5%	<0.5%	CSA A123.23-15
Compound Stability (minimum)	116°C (240°F)		CSA A123.23-15