



**USES:
BASE PLY
FLASHING REINFORCING SHEET**

PARATECH GLASS BASE

Commercial Product Data Sheet

Paratech Glass Base is the modified bitumen base ply of the Paratech two-ply modified bitumen roof system. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paratech Glass Base consists of a lightweight random fibrous glass mat impregnated and coated with styrene-butadiene-styrene (SBS) modified bitumen blend and is surfaced with a mineral parting agent.

Contact Siplast for information on approved product uses.

PRODUCT INFORMATION

Application

Refer to the Siplast specifications for detailed application information and slope limitations. Paratech Glass Base is lapped 3 inches (76 mm) side and end.



Storage and Handling

All Siplast roll roofing products should be stored on end on a clean flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

Packaging

Pallet: 41 in x 48 in (104 cm x 122 cm) wooden pallet
 Rolls Per Pallet: 25
 Pallets Per Truckload: 18
 Roll Weight (nominal): 93 lb (42.2 kg)

Listings, Approvals, & Certifications



| | |
|---|---|
| Standards | ASTM D6163 Type I, Grade S; CSA A123.23-15 Type A, Grade 2 |
| Roll Length (nominal) | 49.2 ft (15 m) |
| Roll Width (nominal) | 3.28 ft (1.0 m) |
| Coverage Per Roll (Typical with 3" Side & End Laps) | 1.484 Squares (13.7 m ²) |
| Coverage Weight Per Square (nominal) | 62 lb (3.0 kg/m ²) |
| Laying Lines (nominal) | 3 in (76 mm) Line Color: White |
| Top & Back Surfacing | Mineral Parting Agent |

U.S. TEST STANDARDS

| Property (as Manufactured) | Values / MD | Values / XMD | Test Method |
|--|------------------------|------------------------|-------------|
| Thickness (average) | 90.6 mils (2.3 mm) | | ASTM D5147 |
| Peak Load @ 73.4°F (23°C) (average) | 30 lbf/inch (5.3 kN/m) | 30 lbf/inch (5.3 kN/m) | ASTM D5147 |
| Peak Load @ 0°F (-18°C) (average) | 30 lbf/inch (5.3 kN/m) | 30 lbf/inch (5.3 kN/m) | ASTM D5147 |
| Elongation @ Peak Load 73.4°F (23°C) (average) | 4% | 4% | ASTM D5147 |
| Elongation @ Peak Load 0°F (-18°C) (average) | 3% | 3% | ASTM D5147 |
| Ultimate Elongation 73.4°F (23°C) | 15% | 25% | ASTM D5147 |
| Tear Strength (average) | 40 lbf (0.18 kN) | 40 lbf (0.18 kN) | ASTM D5147 |
| Water Absorption (maximum) | 1% | | ASTM D5147 |
| Low Temperature Flexibility (maximum) | 0°F (-18°C) | 0°F (-18°C) | ASTM D5147 |
| Dimensional Stability (maximum) | 0.2% | 0.2% | ASTM D5147 |
| Compound Stability (minimum) | 225°F (107°C) | | ASTM D5147 |

CANADA TEST STANDARDS

| Property (as Manufactured) | Values / MD | Values / XMD | Test Method |
|--|------------------------|------------------------|----------------|
| Thickness (average) | 2.3 mm (90.6 mils) | | CSA A123.23-15 |
| Strain Energy 23°C (73.4°F) (minimum) | 0.5 kN/m | 0.5 kN/m | CSA A123.23-15 |
| Strain Energy -18°C (0°F) (minimum) | 0.4 kN/m | 0.4 kN/m | CSA A123.23-15 |
| Peak Load @ 23°C (73.4°F) (average) | 5.3 kN/m (30 lbf/inch) | 5.3 kN/m (30 lbf/inch) | CSA A123.23-15 |
| Peak Load @ -18° (0°F) (average) | 5.3 kN/m (30 lbf/inch) | 5.3 kN/m (30 lbf/inch) | CSA A123.23-15 |
| Elongation @ Peak Load 23°C (73.4°F) (average) | 4% | 4% | CSA A123.23-15 |
| Elongation @ Peak Load -18°C (0°F) (average) | 3% | 3% | CSA A123.23-15 |
| Ultimate Elongation 23°C (73.4°F) | 15% | 25% | CSA A123.23-15 |
| Low Temperature Flexibility (maximum) | -18°C (0°F) | -18°C (0°F) | CSA A123.23-15 |
| Dimensional Stability (maximum) | 0.2% | 0.2% | CSA A123.23-15 |
| Compound Stability (minimum) | 107°C (225°F) | | CSA A123.23-15 |