PARATECH GLASS CAP FR TG

Commercial Product Data Sheet

Paratech Glass Cap FR TG is a modified bitumen finish ply of the Paratech two-ply modified bitumen roof system. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paratech Glass Cap FR TG consists of a lightweight random fibrous glass mat impregnated and coated with a styrene-butadiene-styrene (SBS) modified bitumen blend. The top surface is covered with roofing granules and the back surface is coated with an SBS modified bitumen adhesive layer specifically formulated for torch applications with a polyolefin burn-off film bottom surface.

Contact Siplast for information on approved product uses.

USES:
FINISH PLY

Standards	ASTM D6163 Type I, Grade G; CSA A123.23-15 Type A, Grade 1
Roll Length (nominal)	32.6 ft (10 m)
Roll Width (nominal)	39.4 in (1.0 m)
Coverage Per Roll (Typical with 3" Side & End Laps)	0.986 Squares (98.6 ft²) (9.2 m²)
Coverage Weight Per Square (nominal)	107.1 lb (5.2 kg/m²)
Selvedge Width (nominal)	2.95 in (75 mm)
Top Surfacing	Roofing Granules
Back Surfacing	Polyolefin Burn-off Film
Granule Colors	White A-720, White I-720, Bright White (BW), Gray A-9, Gray I-760

PRODUCT INFORMATION

Application

Refer to the Siplast specifications for detailed application information and slope limitations. Paratech Glass Cap FR TG is lapped 3 inches (76 mm) side and end.

Storage and Handling

All Siplast roll roofing products should be stored on end on a clean flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

Packaging

Roll Weight (Nominal): 105 lb (48 kg)

Max Pallet Weight (Typical): 3060 lbs (1388 kg)
Pallets Per Truckload (Typical): 16

Listings, Approvals, & Certifications

c UL us LISTED FM APPROVED

Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.
FM Approved - Refer to RoofNav.com for specific assemblies.

Siplast 14911 Quorum Dr., Suite 600 Dallas, TX 75254
201 Bewicke Ave., Suite 208 North Vancouver, BC, Canada V7M 3M7
Customer Service in North America 1.800.922.8800 www.siplast.com

PARATECH GLASS CAP FR TG

Physical and Mechanical Properties

siplast® With you every step of the way

U.S. TEST STANDARDS

Property (as Manufactured)	Values / MD	Values / XMD	Test Method
Thickness (average)	140 mils (3.5 mm)		ASTM D5147
Peak Load @ 73.4ºF (23ºC) (average)	50 lbf/inch	40 lbf/inch	ASTM D5147
Peak Load @ 0ºF (-18ºC) (average)	115 lbf/in (20.14 kN/m)	100 lbf/in (17.51 kN/m)	ASTM D5147
Elongation @ Peak Load 73.4ºF (23ºC) (average)	5%	5%	ASTM D5147
Elongation @ Peak Load 0ºF (-18ºC) (average)	4%	4%	ASTM D5147
Ultimate Elongation 73.4ºF (23ºC)	25%	35%	ASTM D5147
Tear Strength (average)	40 lbf (0.18 kN)	40 lbf (0.18 kN)	ASTM D5147
Water Absorption (maximum)	1%		ASTM D5147
Low Temperature Flexibility (maximum)	0ºF (-18ºC)	0ºF (-18ºC)	ASTM D5147
Dimensional Stability (maximum)	0.2%	0.2%	ASTM D5147
Compound Stability (minimum)	225°F (107°C)		ASTM D5147
Granule Embedment	1.5 grams per sample Max. avg. loss		ASTM D5147
	2.0 grams per sample Max. individual loss		

CANADA TEST STANDARDS

Property (as Manufactured)	Values / MD	Values / XMD	Test Method
Thickness (average)	3.5 mm (140 mils)		CSA A123.23-15
Strain Energy 23ºC (73.4ºF) (minimum)	0.5 kN/m	0.5 kN/m	CSA A123.23-15
Strain Energy -18ºC (0ºF) (minimum)	0.4 kN/m	0.4 kN/m	CSA A123.23-15
Peak Load @ 23ºC (73.4ºF) (average)	8.8 kN/m	7.0 kN/m	CSA A123.23-15
Peak Load @ -18º (0ºF) (average)	20.1 kN/m	17.6 kN/m	CSA A123.23-15
Elongation @ Peak Load 23ºC (73.4ºF) (average)	5%	5%	CSA A123.23-15
Elongation @ Peak Load -18ºC (0ºF) (average)	4%	4%	CSA A123.23-15
Ultimate Elongation 73.4ºF (23ºC)	25%	35%	CSA A123.23-15
Low Temperature Flexibility (maximum)	-18ºC (0ºF)	-18ºC (0ºF)	CSA A123.23-15
Dimensional Stability (maximum)	0.2%	0.2%	CSA A123.23-15
Compound Stability (minimum)	107ºC (225ºF)		CSA A123.23-15
Granule Embedment	1.5 grams per sample Max. avg. loss		CSA A123.23-15
	2.0 grams per sample Max. individual loss		

Siplast 14911 Quorum Dr., Suite 600 Dallas, TX 75254

201 Bewicke Ave., Suite 208 North Vancouver, BC, Canada V7M 3M7

Customer Service in North America 1.800.922.8800 www.siplast.com

PARATECH GLASS CAP FR TG

Physical and Mechanical Properties

siplast® With you every step of the way

SOLAR REFLECTANCE / THERMAL EMITTANCE

Property (as Manufactured)	Values	Test Method
*Solar Reflectance (avg.)	0.74	ASTM C1549
*Thermal Emittance (avg.)	0.91	ASTM C1371
*Solar Reflectance Index (avg.)	92	ASTM E1980

*Only applies to Bright White (BW) granule surfaced rolls.