

PRO COLOR FINISH RESIN

Commercial Product Data Sheet



Pro Color Finish Resin is a pigmented, multi-component, fast curing PMMA resin for use in Parapro, Terapro, and Terapro VTS Systems.

Contact Siplast for specific information on approved product uses.

USES: LIQUID FINISH LAYER

Colors	Contact Siplast for Availability of a Specific Color
Pot Life	15 minutes at 68°F (20°C)
Typical Set/Cure Times at 68°F (20°C)	<p>Rainproof: 30 minutes</p> <p>Reay for Next Coat: 45 minutes</p> <p>Stress Resistant: 2 hours</p>
VOC Content	50 g/L (catalyzed)

PRODUCT INFORMATION

Application

Refer to the applicable Siplast Technical or Installers Guide for detailed application information, including application/coverage rates. Product must be catalyzed before use using Pro Catalyst Liquid or Powder. See mixing charts that are supplied with Pro Catalyst products.



Storage and Handling

Store indoors in well-ventilated, cool, dry area away from heat, open fire, ignition sources, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Store jobsite materials on pallets in shaded, well-ventilated area. Cover unshaded areas with reflective tarp that allows air circulation. Standard shelf life is 6 months; product life is reduced when stored at temperatures above 77°F (25°C).

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Packaging: 10 kg (22 lb) resealable metal drums
Units Per Pallet: 60

Listings, Approvals, & Certifications



Current copies of all Siplast Commercial Product Data Sheets & Safety Data Sheets are posted on our website at www.siplast.com
Rev Date 3/2022

MASS AND VOLUME DATA FOR PRO CATALYST LIQUID

NET CONTENTS PER UNIT

2.5 kg	2.25 L	2250 mm	10 cups
Product	Density (kg/L)	Liquid Measure (L/kg)	Liquid Measure (mL/kg)
Pro Catalyst Liquid	1.1 kg/L	0.91 L/kg	910 mL/kg

PRO CATALYST LIQUID MIXING CHART

Resin Quantity	Ambient Temperature 59°F to 95°F (15°C to 35°C)		Ambient Temperature 41°F to 59°F (5°C to 15°C)		Ambient Temperature 32°F to 41°F (0°C to 5°C)	
	Tbsp.	Cups	Tbsp.	Cups	Tbsp.	Cups
1 kg (1 L)	2	n/a	4	n/a	6	n/a
10 kg (10L)	n/a	1	n/a	2	n/a	3

Substrate temperature range for application of Pro Color Finish Resin is 32°F to 95°F (0°C to 35°C)