

# WALLcontrol™ REINFORCED ALUMINUM BUTYL ADHERED FLASHING

## Commercial Product Data Sheet



**USES:**  
**WINDOW & DOOR FLASHING**  
**SUBSTRATE JOINT TREATMENT**  
**WALL TRANSITIONS & PENETRATIONS FLASHING**

### Certifications & Evaluations



<b>Composition</b>	Aluminum topsheet Reinforcement film and grid Butyl adhesive Siliconized release liner	
<b>Product Dimensions</b>	Thickness: 40 mils (1 mm) Roll Length: 50 ft (12.2 m) Roll Widths: 4 in (100 mm) 6 in (150 mm) 9 in (230 mm) 12 in (300 mm)	
<b>Packaging</b>	4 in roll 6 in roll 9 in roll 12 in roll	12 rolls/box 8 rolls/box 4 rolls/box* 4 rolls/box
<small>Box Size</small> 12 in x 12 in x 12 in		

\*Packed in a 9 in x 12 in x 12 in box

### Energy Efficiency & Sustainability

As part of a designed building enclosure system, this product can contribute towards LEED "Optimize Energy Performance" and IEQ "Low Emitting Materials."


### PRODUCT INFORMATION

#### Application and Features


Refer to the Siplast Installation Guide for detailed application information of Siplast WALLcontrol Reinforced Aluminum Butyl Adhered Flashing.



#### Control Category



#### Features




#### Storage, Handling, and Packaging

WALLcontrol Reinforced Aluminum AWB products should be stored between 40°F - 90°F (4.4°C -32.2°C) on a clean, flat surface in dry conditions out of direct exposure to the elements. Pallets should not be double stacked. Material should be handled so that it remains dry prior to and during installation. Use appropriate safety equipment and job-site controls during application and handling. Dispose of unused product and containers in accordance with local, state and federal regulations.

9 in x 12 in x 12 in boxes per pallet: 80  
 12 in x 12 in x 12 in boxes per pallet: 64

# WALLcontrol™ REINFORCED ALUMINUM BUTYL ADHERED FLASHING

Physical and Mechanical Properties



Property (as Manufactured)		Test Method	Min. Value	Typical Values
AIR CONTROL	Material Air Permeance	ASTM E2178 CAN/ULC S741	< 0.004 cfm/sf	0.0002 cfm/sf
	Assembly Air Permeance	ASTM E2357 CAN/ULC S742	< 0.040cfm/sf	0.002 cfm/sf Class A1
	ABAA Evaluation	ABAA S0007	Pass	Pass
WATER CONTROL	Water-Resistive Barrier Acceptance Criteria	ICC ES AC 38	Pass	Pass
	Material Water Penetration Resistance	AATCC 127	No Leakage	55cm for 5 hrs
	Water Penetration Resistance at Fasteners	AAMA 711 Section 5.2	No Leakage	Pass
VAPOR CONTROL	Water Vapor Permeability	ASTM E96/E96M	Method A / B	0.07 / 0.05 US Perms
FIRE CONTROL	Surface Burning Characteristics	ASTM E84	Pass	Class A 5 Flame Spread 125 Smoke Developed
	Assembly Flame Propagation	NFPA 285	Pass	Multiple Assemblies
PHYSICAL PROPERTIES	Peel Adhesive Strength to Substrates	ASTM D3330 (90°)	≥1.5 pli	7.0 pli Plywood 6.0 pli Aluminum 3.0 pli OSB
		ASTM D3330 (180°)	≥5.0 pli	7.7 pli Steel
	Pull Adhesive Strength to Substrates	ASTM D4541	≥16 psi	31 psi Exterior gypsum 30 psi Plywood 27 psi CMU
	Accelerated UV Aging	AAMA 711 Section 5.4 - 7 days	≥1.5 pli	3.2 pli
	Elevated Temperature Exposure	AAMA 711 Section 5.5 - 7 days @ 176°F(80°C) -Level 3	≥1.5 pli	8.5 pli
	Thermal Cycling	AAMA 711 Section 5.6 - 10 days	≥1.5 pli	7.6 pli
	Gap Bridging Ability	ABAA T0004	No visible cracking	Class 1 Type B
	Water Immersion	AAMA 711 Section 5.8	≥1.5 pli	7.8 pli Aluminum

Data is based upon typical product performance and is subject to normal manufacturing and packaging tolerance and variation.

## WARRANTY INFORMATION

Siplast WALLcontrol products are backed by a limited product warranty. Visit [siplast.com](http://siplast.com) to see current published sample warranties, contact your local Siplast Representative, or call toll-free at (800) 922-8800 for more information.